

# Technical Data Sheet

Solutions for LMM-6000 Aerosol



**LMM-6000** is our laser marking material for metals. **LMM-6000** is ethanol based which allows for a fast drying time. It can be used on a variety of bare metal substrates including stainless steel, brass, aluminum, titanium, tin, copper, nickel and the like. If the metal has a **lacquered** coating, the **LMM-6000** marking material **will not work**.

#### Using LMM-6000:

LMM-6000 is ready to use in aerosol can form. **IMPORTANT: Shake can well before using. Allow the agitator ball to rattle for at least 2 minutes. Failure to shake thoroughly will result in spitting and clogging of the nozzle.** For best results, use when aerosol is between 70 and 90 degrees F.

#### Applying:

Clean the surface of the metal so that it is free of any type of lubricants or oils. Hold can approximately 8-12 inches from substrate to be sprayed. Depress valve fully during spray. Apply a thin coat of **LMM-6000** to the metal, try to apply an even coating. Try to cover the area to be marked with a light spray, using two passes. If the material is applied too thick, it will require more power to make the mark. It is important that **LMM-6000** is applied with **an even and thin coat**. Applying **LMM-6000** may require practice to achieve the right coverage. After use, the can nozzle should be cleaned by inverting the can and spraying until mist becomes clear. Any excess material on the nozzle should be cleaned off with water. **We recommend that all CerMark LMM products be applied in a well-ventilated area or spray booth designed to pull air away from user.**

#### Drying:

It is important that the **LMM-6000** is allowed to dry thoroughly. It will air dry in about 2 minutes. This process can be sped up by using an oven, hair dryer or a heat lamp.

#### Marking On Stainless Steel & Other metals:

This step may require some trial and error to optimize your laser with a particular substrate. Keep in mind that all lasers react differently depending on the substrate, the type of laser, the laser's power, dot size, and other factors:

	25 Watt	35 Watt	50 Watt
Power	100%	100%	100%
Speed	10%	15%	20-30%
DPI/PPI	500/500	500/500	500/500

### Marking On Aluminum & Brass:

Softer Metals require more power or slower speeds to obtain a permanent mark. We recommend at least a 50 Watt CO<sub>2</sub> lasers for such metals.

	Brass			Aluminum		
	25 Watt	35 Watt	50 Watt	25 Watt	35 Watt	50 Watt
Power	100%	100%	100%	100%	100%	100%
Speed	2%	4%	6%	4%	7%	10%
DPI/PPI	500/500	500/500	500/500	500/500	500/500	500/500

### Additional Testing Grid (CO<sub>2</sub>) similar testing can be adapted for solid state systems as well

- Set laser power output at 100% or 90% is optional for laser systems over 75 watts.
- Then laser test marks at various speed settings one beside the other.
- Scrub test marks with 3M Scotch-Brite / Medium Duty Scrub Pad to verify durability.
- Based on these results choose the best setting for your application.

If you are using a **YAG** laser, you will need to use about **20-25 Watts** of power and a writing speed between **10-20 inches/second**. Again, you may need to run several tests to optimize the settings for your particular laser, similar to above Testing Grid.

### Storage:

Do not expose to temperatures exceeding 50 degrees C / 120 degrees F.

There are solids and liquids that make up the aerosol marking products. If the aerosol can remains unused for any length of time the liquids and solids will separate, with the solids settling to the bottom of the can. It's best to store the can upside down. When doing so this will prevent the solids from settling on the bottom of the can where the intake stem is located. When this is done it will be easier to prevent the solids from entering the stem before the solids are mixed back into solution with the liquids.

**It's very important to shake the aerosol can for 2 minutes after the rattle ball inside the can has been released.**

It is also recommend that you invert the can after use and spray for a few seconds to clear the system. If you limit this to just a few seconds (3-5) there will be no waste of propellant gases, the aerosol cans have an adequate supply of gas for this procedure.

A simple wipe of the nozzle is recommended so that products doesn't dry over the hole causing a disruption in the spray pattern.

### Limitation of Warranty and Liability

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at [www.ferro.com](http://www.ferro.com). In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.



Solutions for LMM-6000 Aerosol

**Clean up:**

Wash with water or a wet towel or sponge.

**Contact Information:**

To place an order or questions about properties of this product, application techniques or laser settings please call:

800-245-4951

Customer Service & Technical Service Representative

**Limitation of Warranty and Liability**

Ferro believes that the information contained in this document is accurate at the time of its publication. Ferro makes no warranty with respect to the information contained in this document. The information in this document is not a product specification, either in whole or in part. Your use of the information contained in this document and your purchase and use of this Ferro product are at your sole discretion. Downstream users are responsible for determination of the suitability of this product and for testing in specific applications. Nothing in this document shall be construed as a license for use that infringes upon any property rights of any third party. Please refer to the Safety Data Sheet (SDS) for safe use, handling and disposal information. All sales by Ferro to you are subject to Ferro's Terms and Conditions of Sale, as amended from time to time and available at [www.ferro.com](http://www.ferro.com). In the event this document conflicts with Ferro's Terms and Conditions of Sale, Ferro's Terms and Conditions of Sale shall control.